



OLI-BEIZE Color - Wood stain Color -

Product description

Ready-to-use, very quick drying, intermixable, pigmented, solvent-based stain series in RAL, NCS and Sikkens colours for a transparent coloured surface treatment, with which you can achieve brilliant effects. For spray application.

Properties

- excellent colour depth
- quick drying
- good wetting
- no surface roughening
- application by spray gun
- intermixable
- highly lightfast

Areas of application

Suitable for all common hardwoods and softwoods in the interior. Particularly recommendable for light-coloured wood types, such as maple, birch, ash tree and spruce.

Ordering information

OLI-BEIZE Color					
- Wood stain Color -					
		Ordering code			
1615/120	Yellow	325 572 03			
1615/342	Red	325 555 07			
1615/571	Blue	325 556 03			
1615/689	Green	325 557 18			
1615/799	Black	325 529 04			
1615/900	White	325 531 06			
Container sizes	30 / 10 / 3 / 1 ltrs				
Thinner	LMB 0033	913 734 04			

Labelling

For labelling details and safety instructions, please refer to our safety datasheet at www.oli-lacke.de.

Technical data

Shelf-life in factory sealed containers:	12 months
Thinner (Brightener):	LMB 0033
Air drying at +23°C/65% rh	
Dust dry:	-
Sandable:	-
Stackable:	-
Overcoatable:	after approx. 30 min

Application methods

	Cup spray gun	Airless /Airmix
Spray pressure (bar)	2,5 – 3,0	60 – 90
Nozzle size (mm)	0,8 – 1,2	0,18 – 0,23
Thinner (%)	–	–
Viscosity (4 mm cup)	ready to use	ready to use
Coverage per coat (g/sqm)	40 – 80	40 – 80



Annotations/Instructions for use

- Stir well before use!
- An optical brightening of the colour shade can be achieved by adding Thinner LMB 0033.
- The colour shade of the wood stain depends on the type of wood, sanding and application method. We therefore recommend a test staining.
- OLI Wood stain Color is overcoatable with all lightfast OLI lacquers. Particularly on light and pastel colour shades, you should only use extremely lightfast OLI-CRYL and OLI-AQUA lacquers.
- The surface must be absolutely dry and free of dirt, oil, grease and sanding dust.

Application technology

Example	Picture frame, birch, stained blue	
1. Gradual sanding	Grit size 120-180	
2. Staining	OLI-Beize Color 1615/571 Blue, 40-80 g/sqm	
3. Drying at 23°C / 65% rel. humidity	overcoatable	
	30 min	
4. Priming	OLI-CRYL 2K Mehrschichtlack 25.50, 100-120 g/sqm	
5. Drying at 23°C / 65% rel. humidity	Dust-dry	Sandable
	20 min	1,5 h
6. Intermediate sanding	Grit size 280	
7. Top coat	OLI-CRYL 2K Mehrschichtlack 25.50, 80-100 g/sqm	
8. Drying at 23°C / 65% rel. humidity	Dust-dry	Stackable
	20 min	Over night

Our verbal and written recommendations for application can only provide non-binding advice. They are based on our experiences and the current state of knowledge with regard to practical use. These recommendations, however, do not release the user from the obligation to test the suitability of the product for the intended purpose and application himself. This statement supersedes all previous versions. Last update: 12.02.2010.