



OLI-BEIZE Rustikal - Wood stain Rustic -

Product description

Ready-to-use, lightfast, quick-drying, pigmented solvent-based stain in wood colours, with which you can accentuate the structure of the wood grain in a considerably darker colour and therefore achieve a rustic look. For application by spray gun or brush.

Properties

- intensive highlighting of the wood grain
- quick drying
- good wetting
- no surface roughening
- application by spray gun or brush
- intermixable
- good lightfastness

Areas of application

Suitable for all common coarsely porous wood types, such as oak, ash tree, mahogany or walnut. The stain can also be used for patination.

Ordering information

OLI-BEIZE Rustikal - Wood stain Rustic -				
	Ordering code			Ordering code
IB 0200 / Ei 205	325 505 03		IB 0200 / Ei 277	325 50706
IB 0200 / Ei 382	325 520 07		IB 0200 / Ei 346	325 502 04
IB 0200 / Ei 252	325 506 18		IB 0200 / Nb 402	325 575 02
IB 0200 / Ei 343	325 500 01		IB 0200 / Ma 335	325 510 04
IB 0200 / Ei 344	325 501 08		IB 0200 / Ma 303	325 509 09
IB 0200 / Er 414	325 573 18		IB 0200 / 378 schwarz	325 516 02
IB 0200 / Kb 404	325 574 06		IB 0200 / Ma 346	325 511 00
Container sizes	30 / 10 / 3 / 1 ltrs		Container sizes	30 / 10 / 3 / 1 ltrs
Thinner/Brightener IB 0200/273 colourless	325 515 06		Thinner/Brightener IB 0200/273 colourless	325 515 06

Labelling

For labelling details and safety instructions, please refer to our safety datasheet at www.oli-lacke.de.

Technical data

Shelf-life in factory sealed containers:	12 months
Thinner (Brightener):	IB 0200/273 colourless
Air drying at +23°C/65% rh	
Dust dry:	-
Sandable:	-
Stackable:	-
Overcoatable:	after approx. 30 min

Application methods

	Cup spray gun	Airless /Airmix	Brush
Spray pressure (bar)	2,5 – 3,0	60 – 90	–
Nozzle size (mm)	0,8 – 1,4	0,18 – 0,23	–
Thinner (%)	–	–	–
Viscosity (4 mm cup)	ready to use	ready to use	ready to use
Coverage per coat (g/sqm)	40 – 80	40 – 80	40 – 80



Annotations/Instructions for use

- Stir well before use!
- An optical brightening of the colour shade can be achieved by adding OLI Wood stain Rustic IB 0200/273.
- The colour shade of the wood stain depends on the type of wood, sanding and application method. We therefore recommend a test staining.
- The surface must be absolutely dry and free of dirt, oil, grease and sanding dust.

Application technology

Example	Davonport, stained oak	
1. Gradual sanding	Grit size 120-150	
2. Staining	OLI-Beize Rustikal IB 0200/Ei 277, 40-80 g/sqm	
3. Drying at 23°C / 65% rel. humidity	overcoatable	
	30 min	
4. Priming	OLI-CRYL 2K Mehrschichtlack 25.50, 100-120 g/sqm	
5. Drying at 23°C / 65% rel. humidity	Dust-dry	Sandable
	20 min	1,5 h
6. Intermediate sanding	Grit size 240	
7. Top coat	OLI-CRYL 2K Mehrschichtlack 25.50, 80-100 g/sqm	
8. Drying at 23°C / 65% rel. humidity	Dust-dry	Stackable
	20 min	Over night

Our verbal and written recommendations for application can only provide non-binding advice. They are based on our experiences and the current state of knowledge with regard to practical use. These recommendations, however, do not release the user from the obligation to test the suitability of the product for the intended purpose and application himself. This statement supersedes all previous versions. Last update: 12.02.2010.