

OLI-AQUA GEL 15.60



Product description

Very high-build, water-based and thixotropic gel for application by spatula that can be applied as ultra-quick primer for rational coating within one day, or as particularly high-build and levelling intermediate coat after the first lacquer sanding. Due to its high level of transparency in combination with the above named properties, OLI-AQUA GEL 15.60 is also ideally suitable as basic primer under glossy parquet sealers.

Properties

- highly thixotropic
- excellent transparency
- suitable for glossy lacquerings
- quick drying
- very high-build
- Giscode W3+

Areas of application

Especially smaller surfaces in private areas that can be completely treated within one day in combination with OLI-AQUA GEL 15.60 - priming coat with spatula, sanding and sealing with only two roller applications of OLI-AQUA sealers. Also suitable as intermediate coat for filling small joints, fissures or dents.

Ordering information

OLI-AQUA GEL 15.60 420 962 01
Container sizes 1 ltr

Binder

High-quality PU dispersion

Shelf-life/Storage

12 months in the factory sealed containers. Storage and transport temperatures are not to exceed +30°C or to fall below +5°C.

Labelling

For labelling details and safety instructions please refer to our safety data sheet at www.oli-lacke.de.

Annotations/Instructions for use

- Stir well before use!
- Apply 1-2 coats of OLI-AQUA GEL 15.60 crosswise by spatula; approx. 20-40g/sqm per cross coat.
- When treating delicate wood types such as beech, maple or ash tree, test the suitability of the gel beforehand: Danger of spatula marks and discolourations.
- Do not pour larger amounts of the gel on the ground during application. Work fractionally!
- An intermediate sanding will be necessary if the intermediate drying time exceeds 12 hours.
- Do not apply at floor temperatures below +15°C.
- Not overcoatable with OLI-AQUA FLEX.

Pretreatment

- a) as priming coat: gradual sanding with grit sizes 80/100/120. The finer the sanding, the lesser the wood roughens up. Before the final sanding, fill the joints with OLI-Fugenkitt joint filler and sanding powder.
- b) as intermediate coat: gradual intermediate sanding with grit sizes 100/120 before the application of the topcoat. The surface must be dry, thoroughly cleaned and free of oil, wax, grease, silicon and sanding dust.

Application

1 Example 1 - as priming coat



Efficient setup with spatula
OLI-AQUA GEL 15.60; 1-2 cross coats; 20-40 g/sqm each



approx. 20 min.

2 Example 2 - as intermediate coat



Before the application of the topcoat
sanding, grit size 100-120



OLI-AQUA GEL 15.60 in cross coats, 20 g/sqm each



approx. 30 min.

Drying

Figures above refer to normal conditions of +20°C and 50% relative humidity.