



# OLI-KS Parkettsiegel 7400 / 7600 / 7800

## Parquet sealer

### Product description

Low-stress solvent-based parquet sealer for parquet and wooden floors subject to intensive wear and heavy changes in dimensions. Classic sealer for sports halls and gymnasium parquet flooring. Available in three gloss levels: matt (7400), semi matt (7600) and glossy (7800). OLI-KS parquet sealer 7400 has been tested in accordance with DIN 18032 part 2.

### Properties

- in compliance with the EU Decopaint Directive
- high abrasion resistance
- exceptionally low odour development
- high wear and scratch resistance
- highly elastic
- Giscode KH 1

### Test Standards

- DIN 71-3 (safe for children's toys)
- DIN 531 60 (saliva and sweat resistant)
- DIN 68861 T B, C (chemical resistance)
- DIN 68861 T4 (scratch resistance)
- free of formaldehyde and aromatic compounds

### Areas of application

Delicate floors subject to severe dimensional changes, such as floating floors, strip flooring, floorboards and parquet on underfloor heating.

### Ordering information

Gloss level	matt (7400)	710 007 07
	semi matt (7600)	710 006 00
	glossy (7800)	710 005 04
Container sizes	30/11/3 litres	
Thinner	V 110	912 601 00

### Binder

High-quality modified synthetic resin

### Shelf-life/Storage

12 months in the factory sealed containers. Storage and transport temperatures are not to exceed + 30 °C.

### Labelling

For labelling details and safety instructions please refer to our safety data sheet at [www.oli-lacke.de](http://www.oli-lacke.de).

### Annotations/Instructions for use

- Shake or stir well before use!
- Application with roller or brush.
- The total quantity applied should be 300 g/sqm in private areas and 360 g/sqm in business areas.
- An intermediate sanding will be necessary if the intermediate drying time exceeds 48 hrs.
- If necessary, you can dilute the product for the first coat with approx. 10% OLI-KS Verdünner V110 thinner.
- Do not seal the parquet at a floor temperature below +15°C.
- Danger of spontaneous combustion! Clean soaked cloths/pads immediately after use or submerge in water.

### Pretreatment

Gradual sanding with grit 80/100/120. The finer the sanding, the lesser the wood roughens up. Before the final sanding process, fill the joints with OLI joint filler and sanding powder. The surface must be dry, thoroughly cleaned and free of oil, wax, grease, silicon and sanding dust.

### Application

#### ① Sealing (1. coat)



OLI-KS parquet sealer, approx. 100-120 g/sqm



approx. 18 hrs



Sanding, grit size 120-150

#### ② Sealing (2. coat)



OLI-KS parquet sealer, approx. 100-120 g/sqm



approx. 18 hrs

#### ③ Sealing (3. coat)



OLI-KS parquet sealer, approx. 100-120 g/sqm



approx. 18 hrs



Fully hardened after 8-10 days

### Drying

Figures above refer to normal conditions of 20°C and 50% relative humidity.

### Care

For maintenance cleaning and care we recommend the use of our high-quality OLI-AQUA Polish series.